



PARSON ADHESIVES, INC.

WOOD BONDING ADHESIVES



PARFIX® Cyanoacrylate Adhesives

PARBOND® Epoxy Adhesives



PARFIX® Cyanoacrylate Adhesives

Product	Item Number	Packing	Viscosity, cps	Cure Speed	Gap Fill	Application
PARFIX 3420	34201	1 oz	3 - 5	Fixture: 3 seconds	0.001"	Very low viscosity, wicking grade with very fast curing speed. Good adhesion to wide variety of surfaces including wood, rubber, plastics, metals, concrete, etc.
	34202	2 oz				
	34208	8 oz				
	34206	1 lb				
	34200	44 lb				
PARFIX 3401	34011	1 oz	100 - 120	Fixture: 4 seconds	0.006"	Medium Viscosity with good gap filling capability. Excellent adhesion to wide variety of surfaces such as wood, plastics, rubber, metals, concrete, etc.
	34012	2 oz				
	34018	8 oz				
	34016	1 lb				
	34010	44 lb				
PARFIX 3416	34161	1 oz	1,200 - 1,500	Fixture: 6 seconds	0.008"	High Viscosity with very good gap filling capability. Strong adhesion to wide variety of surfaces.
	34162	2 oz				
	34168	8 oz				
	34166	1 lb				
	34160	44 lb				
PARFIX 3422	34221	1 oz	2,400 - 3,000	Fixture: 12 seconds	0.020"	Extra Thick adhesive with excellent gap filling capability. Widely used for wood bonding.
	34222	2 oz				
	34228	8 oz				
	34226	1 lb				
	34220	44 lb				
PARFIX 3454	34541	20 gram	Gel	Fixture: 18 seconds	0.050"	Excellent for vertical or inverted surfaces. Large gap filling capability.
	34542	2 oz				
	34548	8 oz				
	34546	1 lb				
PARFIX 3408	34081	1 oz	3 - 5	Fixture: 9 seconds	0.001"	No odor grade with very low viscosity, wicking grade. Widely used for bonding variety of surfaces.
	34082	2 oz				
	34088	8 oz				
	34086	1 lb				
PARFIX 1155	11552	2 oz 12 oz Aerosol	1 - 2	Activator to increase the cure speed of all the Cyanoacrylate Adhesives.
	11557					
PARFIX 1144	11442	2 oz 6 oz Aerosol	1 - 2	Activator to increase the cure speed of all the cyanoacrylate adhesives.
	11445					
PARFIX 1122	11222	2 oz	1 - 2	De-Bonder to remove cured or uncured Cyanoacrylate Adhesives.
	11229					

PARBOND® Epoxy Adhesives

Product	Item Number	Packing	Viscosity, cps	Color	Shear Strength	Working Time	Application
150 5-Minute Cure	1508	8 oz kit	Mixed Viscosity: 15,500 cps	Clear	3,150 psi	5-15 Minutes	General-purpose epoxy adhesive for wide variety of bonding application.
	1506	16 oz kit					
	1507	1 gal kit					
329 30-Minute Cure	3298	8 oz kit	Mixed Viscosity: 17,500 cps	Clear	2,950 psi	30-45 Minutes	General-purpose adhesive for wide variety of application.
	3296	16 oz kit					
	3297	1 gal kit					



PARSON ADHESIVES, INC.

Sales Office: 3345, Auburn Road, Suite 107, Rochester Hills, MI 48309, USA
Phone (248) 299-5585 • Fax (248) 299-3846

Manufacturing Plant: 2545 Eastside Park Road Evansville, IN 47715 USA

Email: sales@parsonadhesives.com • Web Site: www.parsonadhesives.com